

ZINC RICH COATING FOR LONG TERM PROTECTION AGAINST RUST & CORROSION

Benefits

- 93% Zinc purity, in dry film.
- Provides long term protection.
- May be used on weathered galvanised iron.
- Reacts with metal to replace damaged surfaces.
- Produces a protective barrier against corrosion.
- May be coated or left uncoated.
- Suitable for use on damaged galvanising, steel, welds.
- Touch dry in 30 minutes.

Features

- Uses same principles as hot dip galvanising.
- Touch dry in 30 minutes.
- Excellent adhesion to galvanised metal.
- Suitable for building and structural applications to steel and iron.
- Convenient aerosol.
- Lead and carbonate free.

PRODUCT INFORMATION

DESCRIPTION

Cold Galvanising is a zinc rich coating with a durable film that is 93% zinc in a dry film and provides long term protection against rust and corrosion. Tremco Cold Galvanising reacts with metal to replace damaged surfaces and produces a protective barrier against corrosion using the same principles as hot dip galvanising. Suitable for use on damaged galvanising, steel, welds, wrought iron and other ferrous metals.

PACKAGING

400g Aerosol.

COLOUR

Grey.

TECHNICAL INFORMATION

CHARACTERISTICS

- TOUCH DRY TIME
approx. 30 Minutes
- RECOAT TIME
approx. 8 Hours
- FLASH POINT
-41°C
- ADHESION TO
Galvanised Steel - Excellent
Wrought Iron - Excellent
- HARDNESS
Cure to a hard durable film in 14 days

USAGE GUIDELINES

SURFACE PREPARATION

- Remove loose materials (abrasive sanding or with wire brushing) and dirt until a firm metal base is established.

APPLICATION

- Hold the can upright approximately 25cm from the surface.
- Apply several light coats rather than one heavy coat.
- Apply in light multiple passes to avoid runs and to achieve adequate coverage.

CLEANING

- Mineral Turpentine.



Cold Galvanising

HEALTH AND SAFETY PRECAUTIONS

- Material Safety Data Sheet must be read and understood before use.

TECHNICAL SERVICE

TREMCO has a team of qualified Technical Sales Representatives who provide assistance in the selection and specifications of products. For more detailed information or service and advice call Customer Service on (02) 9638 2755 or fax (02) 9638 2955.

GUARANTEE/WARRANTY

We warrant our products to be free of defects and manufactured to meet published physical properties when tested according to applicable specifications and TREMCO standards.

Under this warranty we will provide at no charge, product to replace any product proven to be defective when applied in accordance with our written instructions and in applications recommended by TREMCO as being suitable for this product.

All claims concerning product defects must be made within 12 months of shipment. Absence of such claims in writing during this period will constitute a waiver of all claims with respect to such product. This warranty is in lieu of any and all other warranties expressed or implied.