

TREMstop PU

**SINGLE PART, FIRE RATED AND
ACOUSTIC POLYURETHANE SEALANT**

Key Benefits Summary

- TREMstop PU offers excellent performance in moving joints
- Exhibits tenacious adhesion once fully cured
- Does not require a primer on most construction materials
- Durable and flexible
- Tested to AS1530.4 and AS4072.1
- Up to 4 Hours Fire Rating

Standards

TREMstop PU meets or exceeds:

- AS1530.4 and AS4072.1
- ASTM C920, Type S, Grade NS, Class 100/50, Use NT, M, A and O.
- US Federal Spec. TT-S-00230C, Class A, Type 2.

PRODUCT INFORMATION

DESCRIPTION

TREMstop PU is a high performance, low modulus, one component, moisture curing, polyurethane sealant.

USAGE/PURPOSE

Typical applications for TREMstop PU:

- Joints between masonry and concrete
- Precast concrete panel joints
- Between drywall and masonry
- Copper pipe and concrete

LIMITATIONS

TREMstop PU is not recommended for:

- Prolonged immersion in water.
- Application over damp or contaminated surfaces
- Exposure to harsh chemicals
- Special architectural finishes without prior testing

PACK SIZE
600ml sge

PRODUCT CODE
245110

COLOURS

Grey
(other colours available on special order)

INSTALLATION - Joint Design

May be used in any vertical or horizontal joint design in accordance with accepted architectural/engineering practices. Joint width should be 4 times anticipated movement but not less than 6.4mm wide.

TECHNICAL INFORMATION

PERFORMANCE (Typical Properties)

- ADHESION IN PEEL**
Concrete 18-22 pli
Aluminium 20-25 pli
- SKIN TIME**
30-90 minutes
- TACK FREE TIME**
3-4 hours
- STAINING & COLOUR CHANGE**
None
- MOVEMENT CAPABILITY**
+/- 35%
- ACCELERATED AGEING**
No adhesive or cohesive failure, nor significant changes after U.V. and cold temperature Bond Test

NOTE: Typical Properties should not be used as specifications.

USAGE GUIDELINES

DIMENSIONS

- Minimum joint size is 6mm x 6mm
- For joints 6mm to 12mm wide the width to depth ratio should be equal (ie: Square)
- Joints 12mm - 25mm the depth should be equal to half the width (ie: 2:1 ratio)

SURFACE PREPARATION

For good adhesion, the joint interface must be sound, clean and dry. Depending on the substrate, or presence of form release agents, masonry waterproofing, dust, loose mortar or laitance, architectural paints or finishes, the joint surface may require a thorough wire brushing, grinding, sandblasting, solvent washing and/or primer.



TREMstop PU

TOOLING & CLEANING

Tooling is recommended immediately after application to ensure firm intimate contact with the joint interface. Dry tooling is preferred although tooling agents can be utilised. Excess sealant and smears adjacent to the joint can be removed with Xylol or Toluol before sealant cures.

JOINT BACKING BOND BREAKING TAPE

Closed cell polyethylene backer rods are preferred as joint backing to control depth of sealant bead. Where depth of joint will prevent use of joint backing, an adhesive backed polyethylene tape should be installed to prevent three-side adhesion.

METHOD OF APPLICATION

TREMstop PU is easy to apply with conventional caulking equipment. Fill joint completely with a proper width-to-depth ratio and tool.

MAINTENANCE

Damaged sealant can be repaired. Consult your Tremco representative for repair procedures.

HEALTH AND SAFETY PRECAUTIONS

Material Safety Data Sheet must be read and understood before use.

TECHNICAL SERVICE

TREMCO has a team of qualified Technical Sales Representatives who provide assistance in the selection and specifications of products. For more detailed information or service and advice call Customer Service on (02) 9638 2755 or fax (02) 9638 2955.

GUARANTEE/WARRANTY

We warrant our products to be free of defects and manufactured to meet published physical properties when tested according to applicable specifications and TREMCO standards.

Under this warranty we will provide at no charge, product to replace any product proven to be defective when applied in accordance with our written instructions and in applications recommended by TREMCO as being suitable for this product.

All claims concerning product defects must be made within 12 months of shipment. Absence of such claims in writing during this period will contribute a waiver of all claims with respect to such product. This warranty is in lieu of any and all other warranties expressed or implied.