

PRODUCT DESCRIPTION

Corflute protects the installed membrane from mechanical damage from other trades during the construction process.

USAGE/PURPOSE

Ideal in protecting the membrane during construction.

PACKAGING

350g/m² 1.2m x 1.8m Sheets

FEATURES & BENEFITS

- Light weight
- Self-supporting
- Easily placed

MECHANICAL PROPERTIES		
Property	Test Method	Result
Tensile Strength	ASTM D638	25 MPa (at yield)
Izod Impact	ASTM D256	134 J/m
Flexural Modulus	ASTM D790	1.1 GPa
Hardness	ASTM D2240	68 (Shore D)
Specific Gravity	ASTM D792	0.910 - 0.925
Drop Dart Impact	NYLEX TM4	50kg cm/mm
Mould Shrinkage	ASTM D955	1-2%

THERMAL PROPERTIES		
Property	Test Method	Result
Heat Deflection	ASTM D696	50°C (temp @ 1.82MPa)
Co-Efficient of Linear Thermal Expansion	ASTM D696	10-15 x 10 ⁻⁵ mm/°C

NOTE: Typical Properties should not be used as Specifications.

CHEMICAL PROPERTIES

Polypropylene Protection Board.

WEATHERABILITY

TREMboard has an appropriate outdoor life of 6 to 12 months when UV exposed.



HEALTH & SAFETY PRECAUTIONS

The Safety Data Sheet (SDS) must be read and understood prior to use.

TECHNICAL SERVICE

Tremco CPG Australia Pty Ltd has a team of Representatives who provide assistance in the selection and specification of products. For more detailed information or service and advice, call Customer Service on (02) 9638 2755 or fax (02) 9638 2955.

GUARANTEE/WARRANTY

Tremco CPG Australia Pty Ltd products are manufactured to rigid standards of quality. Any product which has been applied (a) in accordance with Tremco CPG Australia written instructions and (b) in any application recommended by Tremco CPG Australia, but which is proved to be defective, will be replaced free of charge.

Any information provided by Tremco CPG Australia in this document in relation to Tremco CPG Australia's goods or their use is given in good faith and is believed by Tremco CPG Australia to be appropriate and reliable. However, the information is provided as a guide only, as the actual use and application will vary with application conditions which are beyond our control. Tremco CPG Australia makes no representation, guarantee or warranty relating to the accuracy or reliability of the information and assumes no obligation or liability in connection with the information. To the extent permitted by law, all warranties, expressed or implied are excluded.

CONTACT OUR TEAM

Tremco CPG Australia Pty Ltd
 ABN: 25 000 024 064
 Unit 12, 4 Southridge Street
 Eastern Creek, NSW 2766

P: (02) 9638 2755
 F: (02) 9638 2955
 E: tremco@tremco.com.au