

### PRODUCT DESCRIPTION

Evencure AC is an acrylic modified emulsion used as a curing membrane on freshly poured concrete. Evencure AC meets AS3799 requirements and exhibits excellent durability as a concrete sealer.

### USAGE/PURPOSE

Evencure AC is suitable for curing all freshly laid concrete either smooth or textured, indoors or outdoors.

### FEATURES & BENEFITS

- Dries to a clear finish
- Complies with Australian Standard AS3799
- Achieves water retention of 90% or greater
- Totally water based
- Single pack
- Reduces plastic shrinkage
- Meets low VOC requirements
- Can be applied by spray, roller or brush
- Will not yellow in sunlight
- Eliminates the need for curing by ponded water, damp hessian or polythene sheeting
- Seals concrete surfaces
- Takes most after trades
- Equipment washable in water

### PACKAGING

- 20L Pail
- 200L Drum
- 1000L Tote

### COLOUR

- Milky White

### SHELF LIFE

- 12 months when stored as recommended in original unopened packaging.



### USAGE

- 5m<sup>2</sup>/L

### METHOD OF APPLICATION

Apply Evencure AC to the concrete as soon as the bleed water has gone and the concrete has hardened sufficiently so as not to be marked by the application process. Apply Evencure AC undiluted at a rate of 1 litre per 5m<sup>2</sup>. Best applied by spray, however, may also be applied by brush, roller or broom. If aftertrades need to be applied it is recommended that a period of 28 days from the date of pouring has elapsed before any aftertrades are applied.

**NOTE:** Ensure all equipment is thoroughly cleaned in water.

### HEALTH & SAFETY PRECAUTIONS

The Safety Data Sheet (SDS) must be read and understood prior to use.

### TECHNICAL SERVICE

Tremco CPG Australia Pty Ltd has a team of Representatives who provide assistance in the selection and specification of products. For more detailed information or service and advice, call Customer Service on (02) 9638 2755 or fax (02) 9638 2955.

TYPICAL PHYSICAL PROPERTIES	
PROPERTY	RESULT
Appearance	Milky White Emulsion
Viscosity	20 - 22 seconds (Ford #4)
Solids	30% +/- 1%
Solubility in Water	Totally Soluble
Flash Point	Not applicable
Dry Time	Tack Free
	Hard Dry
	Trafficable
Application Temperature	10°C - 35°C

\*Drying times will vary depending on ambient temperature and relative humidity

### GUARANTEE/WARRANTY

Tremco CPG Australia Pty Ltd products are manufactured to rigid standards of quality. Any product which has been applied (a) in accordance with Tremco CPG Australia written instructions and (b) in any application recommended by Tremco CPG Australia, but which is proved to be defective, will be replaced free of charge.

Any information provided by Tremco CPG Australia in this document in relation to Tremco CPG Australia's goods or their use is given in good faith and is believed by Tremco CPG Australia to be appropriate and reliable. However, the information is provided as a guide only, as the actual use and application will vary with application conditions which are beyond our control. Tremco CPG Australia makes no representation, guarantee or warranty relating to the accuracy or reliability of the information and assumes no obligation or liability in connection with the information. To the extent permitted by law, all warranties, expressed or implied are excluded.

### CONTACT OUR TEAM

Tremco CPG Australia Pty Ltd

ABN: 25 000 024 064

Unit 12, 4 Southridge Street

Eastern Creek, NSW 2766

P: (02) 9638 2755

F: (02) 9638 2955

E: [tremco@tremco.com.au](mailto:tremco@tremco.com.au)