

PRODUCT DESCRIPTION

Evencure XDS NXGEN is a hydrocarbon resin blend cure blended with hardeners and densifiers to create the highest performance curing compound currently available on the Australian market. This unique formulation offers many advantages over existing resin based curing compounds.

USAGE/PURPOSE

Evencure XDS NXGEN is suitable for curing all freshly laid concrete either smooth or textured, indoors or outdoors.

FEATURES & BENEFITS

Due to its unique formulation and blend of resins, Evencure XDS -NXGEN will begin to break down after 7 days and, if applied at the specified application rates, will totally oxidise and leave the surface, subject to UV exposure, within 45 - 55 days of the application. This reduces the need for surface cleaning in preparation for after trades

- Complies with Australian Standards AS3799
- Achieves water retention of 90% or greater
- Increased abrasion and impact resistance
- Contains no wax
- Eliminates the need for curing by ponded water, damp hessian or polythene sheeting
- Reduces concrete dusting and plastic shrinkage
- One coat application
- Can be removed, if required, by ConClena (stripper/degreaser)
- Equipment washable in water
- Available as Type 1 (Clear), Type 1-D (Fugitive dye) and Type 2 (White)
- Densification of the surface for chloride protection

PACKAGING

- 20L Pail
- 200L Drum
- 1000L Tote

COLOUR

Milky homogeneous liquid or with red fugitive dye



SHELF LIFE

12 months when stored as recommended in original unopened packaging.

USAGE

5m²/L

METHOD OF APPLICATION

Apply Evencure XDS NXGEN to the concrete as soon as the bleed water has gone and the new concrete has hardened sufficiently so as not to be marked by the application process. Apply Evencure XDS NXGEN undiluted at a rate of 1 litre per 5m². Best applied by spray, however, may also be applied by brush, roller or broom.

HEALTH & SAFETY PRECAUTIONS

The Safety Data Sheet (SDS) must be read and understood prior to use.

TECHNICAL SERVICE

Tremco CPG Australia Pty Ltd has a team of Representatives who provide assistance in the selection and specification of products. For more detailed information or service and advice, call Customer Service on (02) 9638 2755 or fax (02) 9638 2955.

TYPICAL PHYSICAL PROPERTIES

PROPERTY		RESULT
Appearance		Milky homogeneous liquid or with red fugitive dye
Viscosity		0.22 Pascal seconds
Solids		29% or greater
Solubility in Water		Soluble
Flash Point		160°C>
Dry Time	Tack Free	1 - 3 Hours
	Hard Dry	4 - 8 Hours
	Trafficable	24 Hours
Application Temperature		10°C - 35°C

*Drying times will vary depending on ambient temperature and relative humidity

GUARANTEE/WARRANTY

Tremco CPG Australia Pty Ltd products are manufactured to rigid standards of quality. Any product which has been applied (a) in accordance with Tremco CPG Australia written instructions and (b) in any application recommended by Tremco CPG Australia, but which is proved to be defective, will be replaced free of charge.

Any information provided by Tremco CPG Australia in this document in relation to Tremco CPG Australia's goods or their use is given in good faith and is believed by Tremco CPG Australia to be appropriate and reliable. However, the information is provided as a guide only, as the actual use and application will vary with application conditions which are beyond our control. Tremco CPG Australia makes no representation, guarantee or warranty relating to the accuracy or reliability of the information and assumes no obligation or liability in connection with the information. To the extent permitted by law, all warranties, expressed or implied are excluded.

CONTACT OUR TEAM

Tremco CPG Australia Pty Ltd

ABN: 25 000 024 064

Unit 12, 4 Southridge Street

Eastern Creek, NSW 2766

P: (02) 9638 2755

F: (02) 9638 2955

E: tremco@tremco.com.au