

PRODUCT DESCRIPTION

TREMboard protects the membrane during backfill and from other trades during the construction process.

USAGE/PURPOSE

Ideal in protecting the membrane during construction.

FEATURES & BENEFITS

- Light weight
- Up to 43% greater puncture resistance than coreflute board
- Available in rolls only

PACKAGING

1.2m x 50m Rolls

TYPICAL PHYSICAL PROPERTIES		
Property	Test Method	Result
Tensile Strength	ASTM D638	22-31 MPa (at yield)
Elongation	ASTM D638	10-1200% (at break)
Flexural Modulus	ASTM D790	1000-1500 MPa
Hardness	ASTM D2240	73 (Shore D)
Water Absorption	ASTM D570	<0.01%
Max Deformation	ASTM D4833	24mm
Load at Max ^	ASTM D4833	120 N
Load	ASTM D2412	876N (20% Compression)
Stress at	ASTM D2412	38kPa (20% Compression)
Young's Modulus	ASTM D2412	0.43MPa

NOTE: Typical Properties should not be used as Specifications

CHEMICAL PROPERTIES

TREMboard has outstanding chemical resistance to most organic and inorganic chemicals. However it is liable to attack by oxidising agents such as bromic acid, sulfuric acid, nitric acid and benzene.

WEATHERABILITY

TREMboard has an appropriate outdoor life of 6 to 12 months when subject to UV exposure.

HEALTH & SAFETY PRECAUTIONS

The Safety Data Sheet (SDS) must be read and understood prior to use.

TECHNICAL SERVICE

Tremco has a team of Representatives who provide assistance in the selection and specification of products. For more detailed information or service and advice, call Customer Service on (02) 9638 2755 or fax (02) 9638 2955.

GUARANTEE/WARRANTY

TREMCO products are manufactured to rigid standards of quality. Any product which has been applied (a) in accordance with TREMCO written instructions and (b) in any application recommended by TREMCO, but which is proved to be defective, will be replaced free of charge.

Any information provided by TREMCO in this document in relation to TREMCO's goods or their use is given in good faith and is believed by TREMCO to be appropriate and reliable. However, the information is provided as a guide only, as the actual use and application will vary with application conditions which are beyond our control. TREMCO makes no representation, guarantee or warranty relating to the accuracy or reliability of the information and assumes no obligation or liability in connection with the information. To the extent permitted by law, all warranties, expressed or implied are excluded.