

PRODUCT DESCRIPTION

An SBS-modified bitumen, torch applied, elastomeric joint waterproofing material, for use in conjunction with Tremco's TREMproof Torch 3000, 4000, 4000M, or Anti-root offering.

USAGE/PURPOSE

Typical applications for TREMproof Torch 5000 EXJ include:

- Detailing expansion/movement joints in TREMproof Torch waterproofing/roofing applications.

PACKAGING

1 m (W) x 10 m (L) x 5 mm (T)

COLOURS

Black

LIMITATIONS

Not suited for use in areas subject to environment temperatures greater than 70°C.

SHELF LIFE

12 months when stored as recommended in original unopened packaging.

STORAGE

Store in a dry cool place in an upright position in original, undamaged packaging.

HEALTH & SAFETY PRECAUTIONS

The Safety Data Sheet (SDS) must be read and understood prior to use.

TECHNICAL SERVICE

Tremco CPG Australia Pty Ltd has a team of Representatives who provide assistance in the selection and specification of products. For more detailed information or service and advice, call Customer Service on (02) 9638 2755 or fax (02) 9638 2955.



GUARANTEE/WARRANTY

Tremco CPG Australia Pty Ltd products are manufactured to rigid standards of quality. Any product which has been applied (a) in accordance with Tremco CPG Australia written instructions and (b) in any application recommended by Tremco CPG Australia, but which is proved to be defective, will be replaced free of charge.

Any information provided by Tremco CPG Australia in this document in relation to Tremco CPG Australia's goods or their use is given in good faith and is believed by Tremco CPG Australia to be appropriate and reliable. However, the information is provided as a guide only, as the actual use and application will vary with application conditions which are beyond our control. Tremco CPG Australia makes no representation, guarantee or warranty relating to the accuracy or reliability of the information and assumes no obligation or liability in connection with the information. To the extent permitted by law, all warranties, expressed or implied are excluded.

CONTACT OUR TEAM

Tremco CPG Australia Pty Ltd
 ABN: 25 000 024 064
 Unit 12, 4 Southridge Street
 Eastern Creek, NSW 2766

P: (02) 9638 2755

F: (02) 9638 2955

E: tremco@tremco.com.au

TYPICAL PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	TYPICAL VALUES
Thickness	ASTM D374	5mm
Cold Bending Temperature	NEN 2090	-20°C
Elongation	ASTM D412	+/- 15%
Resistance to Hydrostatic Water Pressure	DIN 52133	Exceeds 0.1 MPa over 24 Hours