


Grey waterproofing slurry

- waterproofing against active or passive water pressure
- for concrete and masonry
- efflorescence-free
- applicable by spray equipment
- suitable also for corrosion protection for reinforcing steel
- approved for potable water

| | | |
|-----------------------------|---|---|
| Compressive Strength | class R3 ≥ 25 MPa |  0761 |
| Chloride ion content | ≤ 0.05% | |
| Adhesive bond | ≥ 2.0 MPa | Vandex Isoliermittel-GmbH Industriestr. 21 DE-21493 Schwarzenbek 09 005 EN 1504-3:2005/ZA.1a CC fine mortar for structural repair (based on hydraulic cement) |
| Carbonation resistance | passed | |
| Modulus of elasticity | ≥ 20 GPa | |
| Thermal compatibility | | |
| Part 1: Freeze thaw with | | |
| de-icing salt immersion | ≥ 2.0 MPa | |
| Part 4: Dry thermal cycling | ≥ 2.0 MPa | |
| Capillary absorption | ≤ 0.5 kg/m ² ·h ^{0,5} | |
| Reaction to fire | class A1 | EN 1504-7:2006/ZA.1a CC fine mortar as reinforcement corrosion protection (based on hydraulic cement) |
| Dangerous substances | complies with 5.4 | |
| Shear resistance | NPD | |
| Corrosion protection | passed | |
| Dangerous substances | complies with 5.3 | |

PRODUCT DESCRIPTION

VANDEX BB 75 is a cementitious, ready-mixed surface waterproofer. It is also suitable as corrosion protection for reinforcing steel.

AREAS OF APPLICATION

- substrates: concrete and masonry
- active or passive waterproofing and protection against water and moisture
- foundations, slabs, retaining walls, etc
- drinking water structures
- corrosion protection for reinforcing steel

PROPERTIES

Owing to its composition of cement, quartz with graded grain-size distribution and selected additives, VANDEX BB 75 is waterproof. It can be employed against active and passive water pressures. The initial and final bonding capability of VANDEX BB 75 is excellent, making it suitable to be applied to horizontal as well as vertical surfaces. It is durable, resistant to frost and heat after setting, but all the same permeable to vapour. VANDEX BB 75 is tested for use in contact with drinking water.

Applied as corrosion protection, it does not only enhance rebar corrosion protection, but also improves adhesion to subsequently applied Vandex repair and coating mortar. It forms a hard coating, is resistant to frost and de-icing salts, allows vapour diffusion and reduces CO₂ penetration.

SURFACE PREPARATION

The substrate to be treated must be sound and even, open-pored, roughened and its surface free from voids, large cracks or ridges. Any adhesion reducing substances like bitumen, oil, grease, remains of paint or laitance must be removed by suitable means. Water leaks must be stopped e.g. with VANDEX PLUG.

Thoroughly moisten the substrate it must be damp but not wet at the time of application. Any surface water on horizontal surfaces must be removed.

Brick- and blockwork substrates

Any remaining plaster, render or other substances that could inhibit bonding must be removed back to the substrate. Gypsum, remains of wood or other foreign material must be removed by appropriate means. Loose pointing must be routed out and the substrate cleaned thoroughly.

For application as corrosion protection

Exposed reinforcing steel should be cleaned and the residue

removed by sandblasting or by using other suitable tools (be sure to achieve SA 2½ clean rating in accordance with DIN EN 12944-4 resp. ISO 8501-1). Remove concrete surrounding the corroded steel to a sound substrate. Steel and concrete may be moist.

MIXING

Mix 25 kg of VANDEX BB 75 with 4.5–6 litres of tap water in a clean container for at least 3 minutes to a lump-free, homogeneous consistency. Use a mechanical mixer.

APPLICATION

VANDEX BB 75 is applied with brush, trowel or suitable spray equipment.

A maximum of 2 mm (approx. 4 kg/m²) can be applied in one working cycle. In most cases the application of more than one coat is recommended; please refer to relevant specification. It is recommended to apply the next coat whilst the previous coat is still damp on the surface. The previous coat must not be damaged during application of the following coat. The waiting time before applying the following coat depends on local climatic conditions such as humidity, temperature, etc. The previous coat is textured by suitable means whilst still plastic to form a key. To maintain workability of the material do not add water, simply re-stir the mixture.

Brush application

Ensure that all cavities in the substrate are filled.

Trowel application

First a scratch coat is applied for maximum adhesion to the substrate, working from the bottom up. Ensure that all cavities in the substrate are filled in order to exclude any trapped air.

Spray application

VANDEX BB 75 can be applied with a suitable fine mortar spraying device.

For maximum spray pattern it should be possible to adjust volume of product as well as air pressure and volume. The nozzle diameter is approx. 6 mm.

The first layer of Vandex is applied in a circular motion with the spray nozzle held at a 90° angle to the substrate. The material is then flattened and keyed. The final layer can be left as a spray finish or treated to a specified finish.

Application as corrosion protection

Using brush or roller, carefully apply at least two coats of VANDEX BB

75 with no breaks on prepared steel. Each subsequent coat may be applied after about 1 hour on sufficiently hardened first coat. Depending on temperature, use within 45 to 60 minutes.

Do not apply at temperatures below +5°C, or to a frozen substrate.

CONSUMPTION

Waterproofing:

| Type of water impact | Recommended overall application rate | Total layer thickness (approx.) |
|----------------------|---------------------------------------|---------------------------------|
| Pressureless water | 3-4 kg/m² | 1.5-2mm |
| Water under pressure | 4-6 kg/m² depending on water pressure | 2-3mm |

Corrosion protection: Approx. 2 kg/m² per layer.

Note: Substrate and application conditions have to be observed. Depending on surface roughness, consumption may vary.

CURING

Keep damp for at least 5 days and provide suitable protection against extreme weather conditions (e.g. sun, wind, frost) while setting. The freshly treated surfaces should be protected from rain for a minimum period of 24 h.

PLASTERING/COATING

Surfaces treated with Vandex products which are to be coated or painted should be left to cure for at least 28 days. When a plaster or render finish is required on top of a Vandex treatment it is essential to apply a rough cast of sand and cement on the final Vandex coat while it is still tacky. On hardened Vandex surfaces apply an appropriate bonding agent before rendering. Coatings on top of a Vandex treatment have to be alkali resistant. Decorative coatings applied on the passive water pressure side are recommended to be water vapour permeable.

PACKAGING

25 kg PE-lined paper bag

STORAGE

When stored in a dry place in unopened, undamaged original packaging, shelf life is 12 months.

HEALTH & SAFETY PRECAUTIONS

The Safety Data Sheet (SDS) must be read and understood prior to use.

TECHNICAL SERVICE

Tremco CPG Australia Pty Ltd has a team of Representatives who provide assistance in the selection and specification of products. For more detailed information or service and advice, call Customer Service on (02) 9638 2755 or fax (02) 9638 2955.

GUARANTEE/WARRANTY

Tremco CPG Australia Pty Ltd products are manufactured to rigid standards of quality. Any product which has been applied (a) in accordance with Tremco CPG Australia written instructions and (b) in any application recommended by Tremco CPG Australia, but which is proved to be defective, will be replaced free of charge.


Any information provided by Tremco CPG Australia in this document in relation to Tremco CPG Australia's goods or their use is given in good faith and is believed by Tremco CPG Australia to be appropriate and reliable. However, the information is provided as a guide only, as the actual use and application will vary with application conditions which are beyond our control. Tremco CPG Australia makes no representation, guarantee or warranty relating to the accuracy or reliability of the information and assumes no obligation or liability in connection with the information. To the extent permitted by law, all warranties, expressed or implied are excluded.

| TECHNICAL DATA | | | |
|---|---------------------------|--|--|
| Exposure classes according to EN 206-1:2013 | | Carbonation Chlorides without seawater Chlorides from seawater Frost attack with/without de-icing agent | XC1, XC2, XC3, XC4 XD1, XD2, XD3 XS1, XS2, XS3 XF1, XF2, XF3, XF4 |
| Appearance | | grey powder. VANDEX BB 75 is not a decorative material | |
| Density of wet mix | [kg/l] | approx. 2.0 | |
| Workability at 20°C | [min] | approx. 45 | |
| Setting time at 20°C | [h] | approx. 5–8 | |
| Compressive strength 28 d | [MPa] | approx. 40 | |
| Bending tensile strength 28 d | [MPa] | approx. 6 | |
| Static modulus of elasticity 28 d | [GPa] | approx. 28 | |
| Capillary absorption | [kg/m²·h ^{0.5}] | 0.06 | |
| Further data | | refer to CE marking | |
| All data is averaged from several tests under laboratory conditions. In practice, climatic variations such as temperature, humidity, and porosity of substrate may affect these values. | | | |

The information contained herein is based on our long-term experience and the best of our knowledge. We can, however, make no guarantee since for a successful outcome, all circumstances in an individual case must be taken into consideration. Indications of quantities required are only averages which certain cases might be greater.



Part of



Construction Products Group

HEAD OFFICE:
Tremco CPG Australia Pty Ltd
ABN: 25 000 024 064
Unit 12, 4 Southridge Street,
Eastern Creek, NSW 2766
P: (02) 9638 2755
E: tremco@tremco.com.au
www.tremco.com.au

